CENTURION REFRACTORIES (PTY) LTD

PRODUCT DATA

| PRODUCT NAME | CENTURCAST 14 | |
|---|---------------|-----------------|
| CHEMICAL ANALYSIS | | |
| CHEWICAL ANALYSIS | | |
| SiO ₂ | % | 43.40 |
| Al_2O_3 | % | 47.60 |
| Fe ₂ O ₃ | % | 1.51 |
| TiO ₂ | % | 1.39 |
| CaO + MgO | % | 5.10 |
| $K_2O + Na_2O$ | % | 0.21 |
| Cr_2O_3 | % | - |
| PHYSICAL PROPERTIES | | |
| Bulk Density Dried @ 110 °C | g/cm3 | 2.1 |
| Cold Crushing Strength Dried @ 110 °C | Мра | 65.00 |
| Cold Crushing Strength Fired to 1000 °C | Мра | 75.00 |
| Maximum Particle Size | mm | 6 |
| | °C | 1400 |
| | | 0.00 |
| Permanent Linear change fired to 1000 °C | % | - 0.20 |
| Maximum Service Temperature Permanent Linear change fired to 1000 °C Thermal Conductivity @ 1000 °C | % W/mK | 1.00 |
| Permanent Linear change fired to 1000 °C | | |
| Permanent Linear change fired to 1000 °C Thermal Conductivity @ 1000 °C ADDITIONAL INFORMATION | | |
| Permanent Linear change fired to 1000 °C Thermal Conductivity @ 1000 °C ADDITIONAL INFORMATION Water Addition | W/mK | 1.00 |
| Permanent Linear change fired to 1000 °C Thermal Conductivity @ 1000 °C | W/mK | 1.00 10 - 12 |

THIS DATA IS BASED ON AVERAGE VALUES AND SHOULD NOT BE TAKEN AS A GUARANTEED SPECIFICATION. IT IS SUBJECT TO REASONABLE VARIATION.

WHERE A PROPERTY IS CRITICAL, CONFIRMATION SHOULD BE OBTAINED FROM CENTURION REFRACTORIES.