

CENTURION REFRACTORIES_{(PTY) LTD}

PRODUCT DATA

PRODUCT NAME CENTURCAST 18 Cr MEX		
CHEMICAL ANALYSIS		
SiO ₂	%	2,2
Al ₂ O ₃	%	90
Fe ₂ O ₃	%	0,5
TiO ₂	%	1,4
CaO + MgO	%	2,30
K ₂ O + Na ₂ O	%	0,45
Cr ₂ O ₃	%	3,00
PHYSICAL PROPERTIES		
Bulk Density Dried @ 110 °C	g/cm3	2,95
Cold Crushing Strength Dried @ 110 °C	Mpa	70
Cold Crushing Strength Fired to 1000 °C	Mpa	95
Maximum Particle Size	mm	6
Maximum Service Temperature	°C	1800
Permanent Linear change fired to 1000 °C	%	0
Thermal Expansion at 1000°C	%	0,87
Thermal Conductivity @ 1000 °C	W/mK	2,40
ADDITIONAL INFORMATION		
Water Addition	%	4 - 5
Shelf Life	months	6
Packaging Size	kg	25
No. bags per pallet		40
DESCRIPTION High Alumina castable with Chrome oxide and SSW addition.		
APPLICATION Launders and Spouts		

THIS DATA IS BASED ON AVERAGE VALUES AND SHOULD NOT BE TAKEN AS A GUARANTEED SPECIFICATION. IT IS SUBJECT TO REASONABLE VARIATION.

WHERE A PROPERTY IS CRITICAL, CONFIRMATION SHOULD BE OBTAINED FROM CENTURION REFRACTORIES.